

# Product Data Sheet

## Luminy® D120

**Revision date** 27 March 2024  
**Page** 1 of 2  
**Date previous version** 07 July 2022  
**Version & language** 11/0966 - EN  
**Product availability** Global  
**Product status** Commercial

### PRODUCT DATA SHEET

#### LUMINY® D120

Interested in solutions for bioplastics? Please contact us at

🌐 [www.totalenergies-corbion.com](http://www.totalenergies-corbion.com) ✉ [pla@totalenergies-corbion.com](mailto:pla@totalenergies-corbion.com)

### DESCRIPTION

PLA is a biobased polymer derived from natural resources and offers a significant reduction in carbon footprint compared to oil-based plastics. Luminy® D120 is a high heat, medium viscosity, PLA homopolymer suitable for nucleation and full stereocomplex PLA. The typical Luminy D120 ratios are 3-7% for nucleation and 35-50% for full stereocomplex, in combination with PLLA homopolymers.

### TYPICAL PROPERTIES<sup>1</sup>

Physical properties	Method	Typical value
Density	Literature value	1.24 g/cm <sup>3</sup>
Melt flow index	ISO 1133-A (190°C/2.16kg)	10 g/10 min
Melt flow index	ISO 1133-A (210°C/2.16kg)	23 g/10 min
Stereochemical purity	TotalEnergies Corbion method	≥ 99% (D-isomer)
Appearance	Visual	Crystalline white pellets
Residual monomer	TotalEnergies Corbion method	≤ 0.5%
Water / moisture	Coulometric Karl-Fischer	≤ 400 ppm
Melting temperature	DSC	175°C
Glass transition temperature	DSC	60°C
Mechanical properties	Method	Typical value
Tensile modulus	ISO 527-1	3500 MPa
Tensile strength	ISO 527-1	50 MPa
Elongation at break	ISO 527-1	≤ 5%
Charpy notched impact, 23°C	ISO 179-1eA	≤ 5 kJ/m <sup>2</sup>

<sup>1</sup> Typical properties, not to be interpreted as specifications

### PROCESSING INFORMATION & RECOMMENDATIONS


It is recommended to be in contact with a TotalEnergies Corbion processing expert to discuss exact processing options.

### MOISTURE & PRE-DRYING

It is recommended to dry Luminy® D120 from the packaging for 4-6 hours at 100°C. Drying of semicrystalline PLA homopolymer can be performed in a desiccant hot air dryer, with a dew point of -40°C or less. It is recommended to reduce the moisture content before melt processing to a level less than 250ppm and preferably less than 100 ppm, measured by e.g. Karl-Fischer or Brabender aquatrac method. Predrying is in particular important prior to injection molding, film and sheet production. Moisture causes hydrolysis of the PLA homopolymer during melt processing, resulting in reduced mechanical performance in the final part.

### PACKAGING & STORAGE CONDITIONS

Luminy® D120 is available in 700 kg aluminum-lined octabins and 25 kg sample bags (moisture level not guaranteed for sample bags). It is recommended to store PLA polymer in its closed, original moisture-barrier packaging at temperatures below 50°C. Storage in direct sunlight should be avoided. The supplied PLA polymer pellets are typically semi-crystalline, unless otherwise stated.



© Copyright 2022 TotalEnergies Corbion. All rights reserved. No part of this publication may be copied, downloaded, reproduced, stored in a retrieval system or transmitted in any form by any means, electronic, mechanical photocopied, recorded or otherwise, without permission of the publisher. No representation or warranty is made as to the truth or accuracy of any data, information or opinions contained herein or as to their suitability for any purpose, condition or application. None of the data, information or opinions herein may be relied upon for any purpose or reason. TotalEnergies Corbion disclaims any liability, damages, losses or other consequences suffered or incurred in connection with the use of the data, information or opinions contained herein. In addition, nothing contained herein shall be construed as a recommendation to use any products in conflict with existing patents covering any material or its use. TotalEnergies is a trademark owned and registered by TotalEnergies SE, used under license by TotalEnergies Corbion BV. CORBION is a trademark owned and registered by CORBION N.V. used under license by TotalEnergies Corbion BV.

# Product Data Sheet

## Luminy® D120

**Revision date** 27 March 2024  
**Page** 2 of 2  
**Version & language** 11/0966 - EN

### COMPOSTABILITY

Composting of organic waste helps to divert organic waste from landfill or incineration. Composting is a biological process in which organic wastes are degraded by microorganisms into carbon dioxide, water and humus, a soil nutrient. Luminy® PLA polymers are in compliance with the EN-13432 standard. Luminy® D120 has been certified compostable by TUV Austria (OK Compost S478) and by European Bioplastics (Seedling 7W2030) up to a thickness of 2.3 mm. As the compostability of the end product is also dependent on the geometry of product, it is the responsibility of the manufacturer of the end product to ensure compliance with the regulations.



7W2030

### BIOBASED CONTENT

Luminy® D120 has a biobased content of 100% (confidence level 1) and a biobased carbon content of 100% according to EN16785-1 under certificate number DIC-00001. Luminy® D120 is certified 100% biobased according to ASTM D6866 under the USDA Biopreferred program.



PRODUCT  
DIC-00001

### FOOD CONTACT STATUS

In the European Union, Luminy® PDLA polymer additions up to 7% in a compound are compliant with EU commission regulation 10/2011 of 14 January 2011 (and amendments) on plastic materials and articles intended to come into contact with food. Lactic acid is considered a dual use substance, since lactic acid is approved as a food additive (additive number E270). There are no SMLs or SML(T)s for the ingredients used to produce Luminy® PDLA. The regulation does include a migration limit of 10 mg/dm<sup>2</sup> on the overall migration from finished plastic articles into food. It is the responsibility of the manufacturer of the final product, when intended as a food contact product, to determine that the use of the product is safe and also suitable for the intended application. While it is TotalEnergies Corbion's conclusion that the above mentioned polymers are permitted, it is the final product which must meet the given regulations and the manufacturer should take responsibility to check if the final product is in compliance with these regulations.

### NOTICE REGARDING USE RESTRICTIONS

Unless specifically agreed to in writing, TotalEnergies Corbion will not knowingly market any product into any of the following commercial or developmental applications: (1) bottles or preforms, unless specific arrangements on recycling and end-of-life are in place, (2) microbeads used in personal care products, including without limitation, cosmetics or over-the-counter drugs, (3) components of products intended for human or animal consumption or (4) any application that is intended to be used inside the human body.



© Copyright 2022 TotalEnergies Corbion. All rights reserved. No part of this publication may be copied, downloaded, reproduced, stored in a retrieval system or transmitted in any form by any means, electronic, mechanical photocopied, recorded or otherwise, without permission of the publisher. No representation or warranty is made as to the truth or accuracy of any data, information or opinions contained herein or as to their suitability for any purpose, condition or application. None of the data, information or opinions herein may be relied upon for any purpose or reason. TotalEnergies Corbion disclaims any liability, damages, losses or other consequences suffered or incurred in connection with the use of the data, information or opinions contained herein. In addition, nothing contained herein shall be construed as a recommendation to use any products in conflict with existing patents covering any material or its use. TotalEnergies is a trademark owned and registered by TotalEnergies SE, used under license by TotalEnergies Corbion BV. CORBION is a trademark owned and registered by CORBION N.V. used under license by TotalEnergies Corbion BV.